



Albaksan Alaşımlı Bakır

ALBA 280

CHEMICAL COMPOSITION

<u>Cu</u>	<u>Al</u>	<u>Fe</u>	<u>Mn</u>
% rem	nom.13,10%	nom. 4,10 %	nom. 0,5 %

AVAILABLE STANDART

<u>EN</u>	<u>ASTM</u>	<u>AMS</u>	<u>DIN</u>	<u>RWMA</u>
-----------	-------------	------------	------------	-------------

APPLICATIONS:

- Die Material for Forming
- Inserts for Plastic Industry
- Bending or Drawing Operations

SUPPLIED FORM

- Rings
 - Plates
 - Discs
 - Centrifugals
 - Round bars
 - Square bars
 - Rectangular bars
 - Hexagon bars
- * Custom shapes are available upon request.

PHYSICAL PROPERTIES:

Density	Specific Heat	Electrical Conductivity	Electrical Conductivity (I.A.C.S)	Thermal Conductivity
7.2 g/mm ³	0.42 J/g.K			42 W/m.K

MECHANICAL PROPERTIES:

MATERIAL CONDITION	Tensile Strength Rm N/mm ²	Yield Strength Rp 0,2 N/mm ²	Elongation (A5) %	Hardness (Brinell) HB30
	nom. 520	nom. 400	nom. 1	nom. 280